

## TYPICAL PROPERTIES OF GLASS FIBER PEEK

Property	Test Method	U.S. Units	SI Units
<b>Mechanical Properties</b>			
Tensile Strength	ASTM D 638	25,200 psi	174 MPa
Tensile Modulus	ASTM D 638	1,530,000 psi	10,500 MPa
Tensile Elongation at Break	ASTM D 638	2.70%	2.70%
Flexural Strength	ASTM D 790	39,000 psi	269 MPa
Flexural Modulus	ASTM D 790	1,550,000 psi	10,700 MPa
Izod Impact, Notched	ASTM D 256	2 ft-lb/in	107 J/m
Izod Impact, Unnotched	ASTM D 4812	18 ft-lb/in	960 J/m
<b>Physical Properties</b>			
Water Absorption	ASTM D 570	0.10%	0.10%
Specific Gravity	ASTM D 792	1.53	1.53
<b>Thermal Properties</b>			
Heat Deflection Temperature	ASTM D 648	599°F	315°C
Glass Transition Temperature	ASTM D 3417	302°F	150°C
<b>Electrical Properties</b>			
Dielectric Strength	IEC 248	-	175 kV mm <sup>-1</sup>
Dielectric Constant (50Hz 0-150° C)	IEC 250	-	3.7
Volume Resistivity	IEC 93	-	1 x 10 <sup>16</sup> Ω cm

**For inquires or additional information, please call: 1 (281) 255-6855**

© 2010 Drake Research Ltd.

Neither Drake Research Ltd. nor Drake Plastics Ltd. Company makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this information or its use. The user must determine the manner of use and whether any patents or trademarks are infringed.

Data courtesy of [Solvay Advanced Polymers](#).