

VICTREX® ST™ STG45

➤ **Product Description:**

High performance thermoplastic material, unreinforced PolyEtherKetoneEtherKetoneKetone (PEKEKK), semi crystalline, depth filtered granules for injection moulding, standard flow, colour natural/beige.

➤ **Typical Application Areas:**

Applications for high strength and stiffness as well as good ductility at higher temperatures. Chemically resistant to aggressive environments.

➤ **Material Properties**

	CONDITIONS	TEST METHOD	UNITS	TYPICAL VALUE
Mechanical Data				
Tensile Strength	Yield, 23°C	ISO 527	MPa	115
Tensile Elongation	Break, 23°C	ISO 527	%	20
Tensile Modulus	23°C	ISO 527	GPa	4.3
Flexural Strength	23°C	ISO 178	MPa	180
	125°C			110
	140°C			95
	150°C			80
	165°C			50
	185°C			28
	275°C			21
Flexural Modulus	23°C	ISO 178	GPa	4.1
Compressive Strength	23°C	ISO 604	MPa	145
	120°C			90
	200°C			35
Charpy Impact Strength	Notched, 23°C	ISO 179/1eA	kJ m ⁻²	4.0
Izod Impact Strength	Notched, 23°C	ISO 180/A	kJ m ⁻²	6.0
	Unnotched, 23°C	ISO 180/U		n/b
Thermal Data				
Melting Point		ISO 3146	°C	387
Glass Transition (Tg)	Onset	ISO 3146	°C	162
Coefficient of Thermal Expansion	Along flow below Tg	ISO 11359	ppm °C ⁻¹	45
	Average below Tg			55
	Along flow above Tg			105
	Average above Tg			125
Heat Deflection Temperature	1.8 MPa	ISO 75-f	°C	172
Thermal Conductivity	23°C	ISO/CD 22007-4	W m ⁻¹ °C ⁻¹	0.29 *
Flow				
Melt Viscosity	420°C	ISO 11443	Pa.s	220
Miscellaneous				
Density	Crystalline	ISO 1183	g cm ⁻³	1.30
	Amorphous			1.26

Electrical Properties				
Dielectric Strength	2.5mm thickness	IEC 60243-1	kV mm ⁻¹	21
Comparative Tracking Index		IEC 60112	V	150 *
Loss Tangent	23°C, 1 MHz	IEC 60250	n/a	0.004
Dielectric Constant	23°C, 1 kHz	IEC 60250	n/a	3.0

* Result based on 450G

Recommended Processing Conditions	
Drying Temperature / Time	150°C / 3h or 120°C / 5h
Temperature settings	375 / 380 / 385 / 390 / 395°C (Nozzle)
Hopper Temperature	Not greater than 100°C
Mould Temperature	200°C - 220°C (max 250°C)
Runner	Die / nozzle >3mm, manifold >3.5mm
Gate	>1mm or 0.5 x part thickness

Mould Shrinkage and Spiral Flow					
Spiral Flow	395°C nozzle, 200°C tool	1mm thick section	Victrex	mm	160
	415°C nozzle, 220°C tool				190
Mould Shrinkage	395°C nozzle, 200°C tool	Along flow	ISO294-4	%	1.1
		Across flow			1.2
	415°C nozzle, 220°C tool	Along flow			1.4
		Across flow			1.6

Detailed data available on our website www.victrex.com or upon request

victrex®

World Headquarters

Victrex plc, Hillhouse International, Thornton Cleveleys, Lancashire FY5 4QD United Kingdom
 Tel: + (44) 1253 897700 Fax: + (44) 1253 897701 Email: victrexplc@victrex.com

VICTREX PLC BELIEVES THAT THE INFORMATION CONTAINED HEREIN IS AN ACCURATE DESCRIPTION OF THE TYPICAL CHARACTERISTICS AND/OR USES OF THE PRODUCT OR PRODUCTS, BUT IT IS THE CUSTOMER'S RESPONSIBILITY TO THOROUGHLY TEST THE PRODUCT IN EACH SPECIFIC APPLICATION TO DETERMINE ITS PERFORMANCE, EFFICACY AND SAFETY FOR EACH END-USE PRODUCT, DEVICE OR OTHER APPLICATION. SUGGESTIONS OF USES SHOULD NOT BE TAKEN AS INDUCEMENTS TO INFRINGE ANY PARTICULAR PATENT. THE INFORMATION AND DATA CONTAINED HEREIN ARE BASED ON INFORMATION WE BELIEVE RELIABLE. MENTION OF A PRODUCT IN THIS DOCUMENTATION IS NOT A GUARANTEE OF AVAILABILITY. VICTREX PLC RESERVES THE RIGHT TO MODIFY PRODUCTS, SPECIFICATIONS AND/OR PACKAGING AS PART OF A CONTINUOUS PROGRAM OF PRODUCT DEVELOPMENT. VICTREX® IS A REGISTERED TRADEMARK OF VICTREX MANUFACTURING LIMITED. PEEK™, APTIV™, PEEK-ESD™, T-SERIES™, PEEK-HT™ ARE TRADEMARKS OF VICTREX PLC. VICOTE® IS A REGISTERED TRADEMARK OF VICTREX PLC.

VICTREX PLC MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION, A WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR OF INTELLECTUAL PROPERTY NON-INFRINGEMENT, INCLUDING, BUT NOT LIMITED TO PATENT NON-INFRINGEMENT, WHICH ARE EXPRESSLY DISCLAIMED, WHETHER EXPRESS OR IMPLIED, IN FACT OR BY LAW. FURTHER, VICTREX PLC MAKES NO WARRANTY TO YOUR CUSTOMERS OR AGENTS, AND HAS NOT AUTHORIZED ANYONE TO MAKE ANY REPRESENTATION OR WARRANTY OTHER THAN AS PROVIDED ABOVE. VICTREX PLC SHALL IN NO EVENT BE LIABLE FOR ANY GENERAL, INDIRECT, SPECIAL, CONSEQUENTIAL, PUNITIVE, INCIDENTAL OR SIMILAR DAMAGES, INCLUDING WITHOUT LIMITATION, DAMAGES FOR HARM TO BUSINESS, LOST PROFITS OR LOST SAVINGS, EVEN IF VICTREX HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES, REGARDLESS OF THE FORM OF ACTION.

